

# Faculty of Engineering Department of Textile Engineering

# **Study on Drying Machine in Knit Dyeing Industry**

Course Code: **TE 417**Course Title: **Project (Thesis)** 

#### Submitted By:

Name	ID No.
Md. Sahid Sharker	152-23-4384
Md. Shahidul Islam Khan	152-23-4432

Supervised To: Tanvir Ahmed Chowdhury Assistant Professor

A thesis submitted in partial fulfillment of the requirement for the **Degree** of Bachelor of Science in Textile Engineering

Advance in Textile Wet Processing

April, 2018

# Study on Drying Machine in Knit Dyeing Industry

#### **ACKNOWLEDGEMENT**

Firstly, We express our heartiest thanks and gratefulness to almighty Allah for his divine blessings which makes possible to complete this project successfully.

We are grateful and feel indebtedness to our supervisor **Tanvir Ahmed Chowdhury Assistant Professor,** Department of Textile Engineering, Faculty of Engineering, Daffodil International University. Deep Knowledge and keen interest of our supervisor in the field of textile dyeing and finishing influenced us to carry out this project smoothly. His endless patience, scholar guidance, continual encouragement, constant and energetic supervision, constructive criticism, valuable advice, reading many inferior draft and correcting them at all stages have made it possible to complete this project finally.

We also wish to express our gratitude to **Prof. Dr. S.M Mahbubul Haque Majumder** Department of Textile Engineering, Daffodil International University for his continuous guidance to prepare this project report. We would like to express our thanks to **Prof. Dr. Md. Mahbubul Haque**, Department of Textile Engineering, Faculty of Engineering, and Daffodil International University for his kind help to finish our project report.

We would like to thank our entire course mates in Daffodil International University, Who took part in the discussions while completion of the course works.

Finally, We must acknowledge with due respect for the constant supports and blessings of our parents and family members.

# **Declaration**

We hereby declare that the work which is being presented in this thesis entitled,

"Study on Drying Machine in Dyeir	ng Industry "is original work of our own, have
not been presented for a degree of materials uses for this project have been	any other university and all the resource of n duly acknowledged.
Md. Sahid Sharker	Date: 14-04-2018
Md. Shahidul Islam Khan	Date: 14-04-2018
This is to certify that the above declarates best of our knowledge.	ration made by the candidates is correct to the
Tanvir Ahmed Chowdhury Supervisor	Date

#### **ABSTRACT**

This aim of the study is to know about drying machine in dyeing industry in details. A lot of processes were observed to conduct this study. Specially the change of diameter and GSM were observed very cautiously. Seven fabrics including single jersey, pique, rib& fleece were selected for this study. The process of changing diameter and GSM were studied very carefully. Finally, the relation between GSM and Temperature, GSM and Machine Speed were critically examined.

# TABLE OF CONTENTS

Contents	Page No
Acknowledgements	iii
Declaration	iv
Abstract	v
CHAPTER 1:	1-3
<ul><li>1.1 Introduction</li><li>1.2 Features of drying</li><li>1.3 Significance of the Study</li></ul>	
CHAPTER 2:	
2.1Dewatering Machine 2.1.1 Objectives of Dewatering Machine 2.2.1 Function of the Machine 2.2.2 Machine Specification 2.2.3 Main parts of the machine 2.2.4 Controlling points or Control system 2.2.5 Operational Parameter 2.2.6 Work instruction of Padder Machine 2.2.7 Limitations and faults of the machin	
2.3 Dewatering Machine forTube fabric	
2.3.1 Squeezing M/C	
2.3.2 Machine Specification	
<ul> <li>2.3.3 Function of the Machine</li> <li>2.3.4 Main parts of the machine</li> <li>2.3.5 Controlling points or Control system</li> <li>2.3.6 Work instruction of Squeezer Machi</li> <li>2.3.7 Parameters used for different types of</li> <li>2.3.8 Working Principle of Squeezing M/O</li> <li>2.3.9 Passage Diagram of the Dewatering</li> <li>2.4 Hydro extractors</li> </ul>	ne of fabric
2.4.1 Function of Hydroextractor	
2.4.2 Feature of Hydroextractor	

2.4.3 Work instruction of Hydroextractor 2.4.4 Working procedure of hydro extractor machine
2.5 Drying
2.5.1 Considering points for selecting a dryer
2.5.2 Features of dryer m/c
2.5.3 Dryer m/c specification
<ul> <li>2.5.4 Main parts of the machine</li> <li>2.5. Parameters used for different types of fabric in dryer</li> <li>2.5.6 Work instruction of gas dryer</li> <li>2.5.7 Working Principle of Dryer</li> <li>2.5.8 Passage Diagram of The fabric in Dryer Machine</li> <li>2.5.9 Faults of the machine</li> </ul>
2.6 Tumble dryer
2.6.1 Feature of Tumble dryer
2.6.2 Machine Specification
2.6.3 Work instruction of Tumble dryer
2.6.4 Working Principle of Tumble dryer
2.6.5 How Automatic Drying Operates
CHAPTER 3:
MATERIALS & METHODS
3.2.Methods
CHAPTER 4:
DISCUSSION OF RESULTS25-28
CHAPTER 5: CONCLUSION
REFERENCE

# **CHAPTER 1**

# **INTRODUCTION**

#### 1.1 Introduction

Drying is a mass transfer process consisting of the removal of water or another solvent<sup>[1]</sup> by evaporation from a solid, semi-solid or liquid. This process is often used as a final production step before selling or packaging products. To be considered "dried", the final product must be solid, in the form of a continuous sheet (e.g., paper), long pieces (e.g., wood), particles (e.g., cereal grains or corn flakes) or powder (e.g., sand, salt, washing powder, milk powder). A source of heat and an agent to remove the vapor produced by the process are often involved. In byproducts like food, grains, and pharmaceuticals like vaccines, the solvent to be removed is almost invariably water.

#### 1.2 Features of drying

- > To dry the fabric
- ➤ To control Shrinkage percentage
- > Basically it is use for wet tube fabric
- > To control over feed
- > To control variation which increase G.S.M.
- > To adjust the tone of fabric
- > To match the fabric color shade

#### 1.3Significance of the Study:

- ❖ The importance of the study is given below:
- ❖ After wet processing the weighted about 300% more than is original weight.
- ❖ Most of this weight is due to the amount of water absorbed by the textiles.
- ❖ To remove this water by direct evaporation /drying large amount of heat energy is required.
- ❖ It is calculated that about 18% of the total cost of wet processing goes for heat generation.
- ❖ So this excess waters removed before evaporation/drying to reduce the cost.
- ❖ To achieve the above mentioned knowledge, I have observed a lot of processes of finishing.

# CHAPTER 2 LITERATURE REVIEW

# 2.5 Drying

Drying is done after de-watering of fabric. In textile finishing unit; dryer uses for dry the knit, woven fabrics and dyed yarn. But the drying process and drying mechanism of yarn and fabrics is different from one to another. The main functions of a textile dryer is to dry the textile fabrics. Drying is defined as a process where the liquid portion of the solution is evaporated from the fabric.

#### 2.5.1 Considering points for selecting a dryer

Following points should consider during buy a dryer.

- 1. Heating methods: The textile fabrics may be heated by gas burner or steam.
- 2. Chamber: Number of chamber.
- 3. Burner: Number of burner.

#### 2.5.2 Features of dryer m/c:

- > To dry the fabric
- > To control Shrinkage percentage
- > Basically it is use for wet tube fabric
- > To control over feed
- > To control variation which increase G.S.M.
- > To adjust the tone of fabric
- > To march the fabric color shade

### 2.5.3 Dryer m/c specification:

> Brand name: Chengfu

➤ Country : China

> Capacity: 06-07 Tons per day

➤ Gas driven m/c

Max 170°c to 180°c GSM 150-170

> Min 120°c to 130°c GSM130-150

### 2.5.4 Main parts of the machine:

- 1. Chamber -3
- 2. Burner -3pcs.
- 3. Belt-3pcs
- 4. Blower fan 6
- 5. Blower(motor-) 3pcs
- 6. Nozzle-99



Fig: Chambers of Dryer

# 2.5.5 Parameters used for different types of fabric in dryer

Types of fabric	GSM	Speed m/min	Temperature ( <sup>0</sup> C)
Single jersey	130-150	8-10	120-130
Single jersey	180-200	5-6	140-150
1×1 Rib	210-250	3-4	160-170
2×2 Rib	210-250	3-4	170-180
Puqea	210-250	3-4	170-180
CVC fabric	160-200	5-6	140-150
Fleece	200-250	3-4	170-180

# 2.5.6 Work instruction of gas dryer

Color	Speed m/min	Temperature ( <sup>0</sup> C)
Light	8-10	120-130
Medium	8-10	120-130
Tarques	5-6	160-170
Deep	3-4	170-180



# 2.5.7 Working Principle of Dryer:

After de-watering then the fabric through the dryer, the main function of the dryer is given below,

- 1. To dry the fabric.
- 2. To control the overfeed system.
- 3. To control the vibration which increase the G.S.M.

This machine contains three chambers. Three mesh endless conveyors are placed lengthwise to the chamber named conveyor net and filter net, each chamber contain a burner, which supply hot air .This hot air is guided through the ducting line by suction fan .There are nozzles placed in between filter net and conveyor net. When the fabric pass on the conveyor net, hot air is supplied to the wet fabric to dry it. There are exhaust fan which such the wet air and deliver to the atmosphere through the ducting line.

# 2.5.8 Passage Diagram of The fabric in Dryer Machine




Fig: Passage Diagram of The fabric in Dryer Machine.

#### 2.5.9 Faults of the machine:

- ➤ Create Shade variation due to over high temperature & less Speed of the machine
- > Sometimes Fabrics are burnt for high temperature of low GSM fabrics

# CHAPTER 3 MATERIALS & METHODS

#### `3.1 Materials:

We have taken the following samples for our study

Fabric Type	GSM	Temperature	Machine Speed
Single jersey Fabric	160	120 °C	10
Single jersey Fabric	170	130 °C	11
Single jersey Fabric	160	120 °C	10
Single jersey Fabric	150	140 °C	11
Single jersey Lycra Fabric	175	130 °C	9
2×1 Lycra Rib Fabric	250	180 °C	7
2×1 Lycra Rib Fabric	240	130 °C	7
1 <u>×</u> 1 Rib Fabric	160	160 °C	12
Single jersey (CVC) Cotton	155	130 °C	14
60%+40% Polyester Fabric			

#### 3.2Methods:

At first wet dyed fabric is feed on the drying machine. Then the fabric is treated by drying machine. After drying the output fabric comes out with change in diameter. We have also observed the temperature and machine speed for the above mentioned fabrics.

Fabric variation = Temperature Variation = machine speed variation.

There are many types of fabric and many types of color use of dyer machine .than all fabric is not same and GSM is different than temperature is different use machine speed is different. Fabric type variation than variation of temperature and machine speed,

# CHAPTER 4 DISCUSSION OF RESULTS

# 4.1. Analysis for Diameter Change:

Table-4.1.1: Relation between hot and cooling Dia after drying

Fabric type	GSM	Fabric Dia After Drying (Hot) Inch	Fabric Dia After Drying (Cooling) Inch
Single jersey Fabric	160	34	32
Single jersey Fabric	170	34	32
Single jersey Fabric	160	34	32
Single jersey Fabric	150	34	32
Single jersey Lycra Fabric	175	36	32
2×1 Lycra Rib Fabric	250	35	34
2×1 Lycra Rib Fabric	240	36	35
1 <u>×</u> 1 Rib Fabric	160	35	34
Single jersey (CVC) Cotton	155	34	32
60%+40% Polyester Fabric			

Table-: Relation between hot and cooling Dia after drying

Single jersey Fabric GSM in hot & cool condition difference is two types. Variation is the Fabric variation is GSM than fabric dia after drying hot is the 34 and cooling is the 34 than difference between 2. Single jersey Fabric is variation of Single jersey Lycra Fabric is difference hot and cooling variation. Fabric variation is the different by the fabric gsm variation than hot and cooling system It is the mostly variation of fabric type.


### 4.2. Relation between GSM and Machine Speed:

Table-4.2.1: Relation between GSM and Machine Speed

Fabric type	GSM	Machine
		speed
Single jersey Fabric	160	10
Single jersey Fabric	170	11
Single jersey Fabric	160	10
Single jersey Fabric	150	11
Single jersey Lycra Fabric	175	9
2 <u>×</u> 1 Lycra Rib Fabric	250	7
2 <u>×</u> 1 Lycra Rib Fabric	240	8
1 <u>×</u> 1 Rib Fabric	160	12
Single jersey (CVC) Cotton	155	14
60%+40% Polyester Fabric		

Table-: Relation between GSM and Machine Speed

Graph-4.2.2: Relation between GSM X and Machine Speed Y



Graph: Relation between GSM X and Machine Speed Y

Single Jersey fabric is a type of knit textile made from cotton or a cotton and synthetic blend. Some common uses for jersey fabric include t-shirts and winter bedding. The fabric is warm, flexible, stretchy, and very insulating, making it a popular choice for the layer worn closest to the body. Jersey also tends to be soft, making it very comfortable .Other is the single jersey Lycra fabric is use by lycra .Single jersey fabric gsm is 160 and Machine Speed is require 10 but Single jersey lycra fabric gsm 175 and machine speed is 9 .Single jersey and single jersey lycra fabric is different gsm is different so machine speed is different. $2 \times 1$  Lycra Rib fabric gsm is 240 Machine speed is 7 other wise  $1 \times 1$  Rib fabric gsm is 160 Machine speed is use 12.Single jersey (CVC) Cotton 60% + 40% Polyester Fabric gsm is 155 Machine Speed is 14. Fabric Variation with Machine speed variation.


#### **4.2.3.** Relation between GSM and Temperature:

Table-4.2.3: Relation between GSM and Temperature

Fabric type	GSM	Temperature
Single jersey Fabric	160	120 °C
Single jersey Fabric	170	130 °C
Single jersey Fabric	160	120 °C
Single jersey Fabric	150	140 °C
Single jersey Lycra Fabric	175	130 °C
2 <u>×</u> 1 Lycra Rib Fabric	250	180 °C
2×1 Lycra Rib Fabric	240	130 °C
1 <u>×</u> 1 Rib Fabric	160	160 °C
Single jersey (CVC) Cotton	155	130 °C
60%+40% Polyester Fabric		

Table: Relation between GSM and Temperature

**Graph-4.2: 4Relations between GSM X and Temperature** (°C)**Y** 



Graph: Relations between GSM X and Temperature (°C) Y

Relation between GSM and Temperature is the variation by the Fabric type .single jersey fabric gsm by 150 but Temperature is use by 140  $^{\circ}$ C otherwise Single jersey layera fabric gsm 170 but temperature use is 130  $^{\circ}$ C. Variation by the gsm and fabric type than Temperature is up and down need.gsm,

Fabric type is very important of temperature section.2 $\underline{\times}1$  Lycra Rib Fabric is gsm is 240 and Temperature is 180 °C that time is other gsm fabric is  $1\underline{\times}1$  Rib Fabric gsm is 160 but Temperature is 160 °C and Single jersey (CVC) Cotton 60%+40% Polyester Fabric variation of fabric and gsm is 155 and Temperature is 130 °C

So variation is fabric than variation is temperature.

# CHAPTER 5 CONCLUSION

#### **Conclusion:**

This project work basically helps us to meet the knowledge about drying machine. It is a important study in the field of wet processing technology. The study confirmed that drying machine for fabrics and always so obvious for finished fabric. Drying machine is used for bio-polish process which gives fabrics a clear, luster & even surface appearance. It important to identify which Drying machine is more effective for GSM & Fabric diameter. Comparing the two different material ofdryingmachine, it can be said that both not lead to same result.

#### REFERENCE

- 1. <a href="http://en.wikipedia.org/wiki/dryer">http://en.wikipedia.org/wiki/dryer</a>
- 2. <a href="http://www.Swastiktextile.com/dewatering">http://www.Swastiktextile.com/dewatering</a>
- 3. Books.google.com.bd/books?isbn=1434681270
- 4. <a href="http://en.wikipedia.org/wiki/dryer">http://en.wikipedia.org/wiki/dryer</a>(8;59)7.11
- 5. http://textile learner.com(8;59)7.11
- 6. Chemistry& Technology of Fabric Preparation & Finishing- By Dr. Charles Tomasino,Page 66,64
- 7. Introduction to Textile Finishing-By F.T. Marsh, Page-247.